

Technical Data Sheet

Quartz | 20mm



PROPERTY	RESULT	TESTING METHOD
Water Absorption, % by mass	0.04	ASTM C 97
Apparent Density, g/cm ³	2.406	ASTM C 97
Moh's Hardness	6-7	ASTM C 1895
Flexural Strength, MPa		
Dry Condition	66.2	ASTM C 880
Wet Condition	78.5	ASTM C 880
Co-efficient of Linear Thermal Expansion, °C ⁻¹	4.8 X 10 ⁻⁶	ASTM C 372
Abrasion Resistance, H	31.01	ASTM C 241
Resistance to Staining	Not Affected	ASTM C 1378